



74 Kent Street
Brooklyn, New York 11222-1517

Phone (718) 383-5080
Fax (718) 383-7445
E-mail: dllabs@aol.com

Independent Testing and Consulting Laboratory Serving the Coatings, Sealant,
Waterproofing and Building Materials Industries Since 1932

January 5, 2011

Tagawa Sangyo Company, Ltd.
1924 Yugeta, Tagawa-shi, Fukuoka-ken,
826-0041 Japan

Attn: **Mr. Nobuyoshi Yukihiro**

Re: DL-16256

OBJECTIVE

To determine the hardness of test panels coated with lime plaster coating materials.

PRODUCTS TESTED

The test panels were coated with pre-mixed lime plaster materials identified as ***Shikkui Bright***, ***Shikkui Classic*** and ***Shikkui Kodai***.

PROCEDURES

The hardness of the lime plaster coated test panels was determined in accordance with procedures outlined in ASTM D 2240 Standard Test Method for Rubber Property – Durometer Hardness.

TEST RESULTS

	<u>Shore A Durometer</u>	<u>Shore D Durometer</u>
<i>Shikkui Bright</i>	99	70
<i>Shikkui Classic</i>	98	65
<i>Shikkui Kodai</i>	99	85

DL Labs, Inc.

A handwritten signature in black ink, appearing to read 'Mario Lazaro, Jr.'.

Mario Lazaro, Jr.
Assistant Technical Director