



74 Kent Street
Brooklyn, New York 11222-1517

Phone (718) 383-5080
Fax (718) 383-7445
E-mail: dllabs@aol.com

Independent Testing and Consulting Laboratory Serving the Coatings, Sealant,
Waterproofing and Building Materials Industries Since 1932

October 26, 2010

Tagawa Sangyo Company, Ltd.
1924 Yugeta, Tagawa-shi, Fukuoka-ken,
826-0041 Japan

Attn: **Mr. Nobuyoshi Yukihiro**

Re: DL-16216R

OBJECTIVE

To determine the fungus resistance of test panels coated with a lime plaster coating material.

PRODUCT TESTED

The test panels were coated with a pre-mixed lime plaster material identified as:

Shikkui Sora (Shikkui Plaster)

PROCEDURES

The fungus resistance of the lime plaster coated test panels was determined in accordance with procedures outlined in:

ASTM D 3273 Standard Test Method for Resistance to Growth of Mold on the Surface
of Interior Coatings in an Environmental Chamber

ASTM D 3274 Standard Test Method for Evaluating Degree of Surface Disfigurement of Paint Films
by Microbial (Fungal or Algal) Growth or Soil and Dirt Accumulation

The ***Shikkui Sora (Shikkui Plaster)*** coated test panels were exposed in the ASTM D 3273 environmental chamber to a mixed fungal spore environment consisting of *Aspergillus niger*, *Aureobasidium pullulans* and *Penicillium*. The coated test panels were exposed for 28 days in the chamber at 88-92°F (31-33°C) and 95% R.H. The front and the back of the exposed test specimens were evaluated on a weekly basis in accordance with ASTM D 3274. The fungus resistance ratings range from 10 for no fungal growth to 0 for complete coverage of the surface area by fungi.

TEST RESULTS

The ***Shikkui Sora (Shikkui Plaster)*** coated test panels did not exhibit any fungal growth on the face or back of the test panels after 28-days of exposure (ASTM Rating 10) while an uncoated pine wood control panel exhibited considerable fungal growth (ASTM Rating 2).

DL Labs, Inc.

A handwritten signature in black ink, appearing to read 'Mario Lazaro, Jr.'.

Mario Lazaro, Jr.
Assistant Technical Director